

Green Diamond Sand Products

Abrasive Products

Typical Screen Analysis

US Sieve Size	1636	1650	2050	3060
6	0	0	0	0
8	0	0	0	0
10	.5	0	0	0
12	4	2	0	0
16	55	27	2	0
20	32	25	20	0
30	7	24	35	0
40	.5	17	26	16
50	0	4	11	59
70	0	.5	4	21
Minus 70	0	.5	2	4
Mil profile	3-4	2.5-3	2-2.5	1-2

Analysis of these product sizes are approximate and could change from time to time.

Typical Application Data

1636 – tanks, vats, structural steel, ships, aggregate exposure, general purpose

1650 – all steel, aggregate exposure, tanks

2050 – mill scale, light paint & rust, light aggregate exposure, cabinets, bridges,
ideal for aluminum

3060 – to effect a smooth surface, high pressure water blast systems, blast cabinets,
non-chattering, feathering, ideal for aluminum