


GREEN  DIAMOND
SAND PRODUCTS

NON FERROUS
TYPICAL SCREEN ANALYSIS

US SIEVE	AFS 85	AFS 100	AFS 115	AFS 130	AFS 145
30	0	0	0	0	0
40	0	0	0	0	0
50	1	1	0	0	0
70	26	18	13	11	1
100	40	35	26	17	9
140	20	24	29	29	39
200	7	10	15	20	24
270	4	7	10	13	15
PAN	2	5	7	10	12
AFS No.	85.2	100.9	115.7	130.4	145.4



FERROUS TYPICAL SCREEN ANALYSYS

US SIEVE	40 X 100	50 X 100	50 X 140	70 X 140	AFS 85
30	0	0	0	0	0
40	13	4	2	0	0
50	35	21	11	1	1
70	32	40	30	34	26
100	14	27	40	46	40
140	6	8	15	17	20
200	0.1	0.1	2	2	7
270	0	0	0.1	0.3	4
PAN	0	0	0.1	0.1	2
AFS No.	49.7	56.5	65.8	70	85.2

